

PATENT ABSTRACTS OF JAPAN

(11)Publication number : **2002-155241**

(43)Date of publication of application : **28.05.2002**

(51)Int.Cl.

C09D201/00
B05D 5/06
B05D 7/24
C09C 1/28
C09C 3/06
C09D 5/00
C09D 7/12
C09D183/07

(21)Application number : **2000-355917** (71)Applicant : **NIPPON PAINT CO LTD**

(22)Date of filing : **22.11.2000** (72)Inventor : **MORIBE MICHIIKO**

(54) BRIGHT COATING COMPOSITION, METHOD FOR FORMING FILM AND MULTILAYERED FILM

(57)Abstract:

PROBLEM TO BE SOLVED: To obtain a bright coating composition having an interference color in a highlight part of a formed film, providing a bright feeling providing dichroism different in hue visually confirmed with an angle viewing the film without causing shadow unevenness and yellow cloudiness even when formed on a light chromatic intermediate coating film layer and without causing filter clogging by the glass flake itself during circulation, to provide a method for forming the film and to obtain a multilayered film. SOLUTION: This bright coating composition comprises a titanium dioxide- coated glass flake having 20-40 μm D50 and $\leq 60 \mu\text{m}$ D90, a flaky pigment comprising a cholesteric liquid crystal polymer and a vehicle.

LEGAL STATUS

[Date of request for examination]

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's
decision of rejection]

[Date of requesting appeal against
examiner's decision of rejection]

[Date of extinction of right]

Copyright (C); 1998,2003 Japan Patent Office

* NOTICES *

JPO and NCIPi are not responsible for any damages caused by the use of this translation.

- 1.This document has been translated by computer. So the translation may not reflect the original precisely.
- 2.**** shows the word which can not be translated.
- 3.In the drawings, any words are not translated.

CLAIMS

[Claim(s)]

[Claim 1] The titanium-dioxide coat glass flake whose D50 is 20-40 micrometers and whose D90 is 60 micrometers or less, the flake-like pigment which consists of a cholesteric-liquid-crystal polymer, and the photoluminescent coating constituent containing a vehicle.

[Claim 2] The photoluminescent coating constituent according to claim 1 whose D90 D50 of said glass flake is 20-35 micrometers, and is 30-50 micrometers.

[Claim 3] The photoluminescent coating constituent according to claim 1 or 2 which said glass flake contains 0.01 to 30% at a solid content mass rate to coating solid content.

[Claim 4] A photoluminescent coating constituent given [claim 1 whose rates of a solid content compounding ratio of said glass flake and said flake-like pigment are 10 / 90 - 90/10 to] in 3 any 1 terms.

[Claim 5] The paint film formation approach of using a photoluminescent coating constituent given in 4 any 1 terms for much more formation from claim 1 at least among the layers which constitute a double layer paint film.

[Claim 6] The paint film formation approach that are the approach of forming the double layer paint film which carries out sequential formation of an under coat coat, a middle-coat coat, a photoluminescent coat, and the clear finishing coat, and said photoluminescent coat is formed from claim 1 on a base material with a photoluminescent coating constituent given in 4 any 1 terms.

[Claim 7] The paint film formation approach according to claim 6 formed from the coating with which said clear finishing coat contains a carboxyl group content polymer and an epoxy group content polymer.

[Claim 8] The double layer paint film obtained from claim 5 by the paint film formation approach given in 7 any 1 terms.

[Translation done.]